

BETADEKOR SAD

Technological instructions no.: 29-7

Safety sheet no.:

29b

Composition:

Polymer binding substances, pigments, modifying additives, fillers, biocide agents (protection against moulds, fungi and algae).

General description:

BETADEKOR SAD is water soluble silicon thinlayer rustic render. It serves for final surface treatment of facades and walls in exterior and interior, of plaster boards and for final surface treatment of base layers of external thermal insulation composite systems (hereinafter ETICS) of STX.THERM line.

Merits:

The renders are delivered in reduced scale of tints (see the current colour card). The hardened layer is permanently flexible. The material contains additives limiting occurrence of algae, fungi and moulds. Formed surface enables washing of polluted places by water stream, eventually with detergents, it has very low surface wettability with significant pearly effect and provides the highest resistance to deposition of dust.

Unit of measure:

kg

Consumption per m²:

BETADEKOR SAD20 - 2,4 to 2,8 kg/m²

BETADEKOR SAD25 - 2,8 to 3,6 kg/m²

BETADEKOR SAD30 - 3,3 to 4,0 kg/m²

Spreading capacity:

7,8 m² / bucket (25 kg) according to the thickness of grain

Grain size:

20, 25, 30

Packing:

The product is packed in 15, 25 kg plastic portable buckets.

Customs code:

3214900000

Colour scheme:

Full colour scale except tint of groups a,b.

Thinning:

Consistency can be adapted by adding of max. 2 % of drinking water.

Bases:

The base must be firm and consistent, cleaned from dust, grease spots and all impurities that could reduce the render adhesive capacity to the base. As suitable are the quality, matured (at least 28 days) lime- cement, polymer-cement renders and sealants, concrete, seamless base layers of ETICS of STX.THERM line (matured minimally 24 hours), plaster boards and treated surfaces of chipboards (interior only), cement-chipboards and cement-fibre boards. Volume unstable bases must firstly be equipped by a backfilling (ALFAFIX S1, S11) and glass mesh layer. Bases with supposed increase of humidity in winter period must be frostproof. In stable, inconsistent and polluted places of bases must be mechanically removed, eventually repaired. Also previous lime or glue paints must be removed by regrating. Bases must be flat with even and natural surface structure with sunk edges. Bases with unsuitable flatness must be repaired, levelled eventually smoothed. Application on bases of cement-lime renders with prevalent lime or carbonate fillers is not recommended. Before application of the final surface treatment the base is treated by water soluble base paint HC-4.

Warning:

The mentioned information are compiled upon current status of technique. They represent general instructions upon our application experience and material test results. However they cannot include local conditions at its application and due to this any legal liability cannot be deduced from them. In doubt or need of solution of specific technical questions please contact us.

Preparation of the material:

Before application the material must be mixed by a quick stirrer (drill adapter) or by a mixer with forced mixing. The material is delivered in paste consistency and does not

require any improvements. Consistency can eventually be adapted by adding of max. 2 % of drinking water. Mixing of any other additives is prohibited.

Workability period:

Not mentioned.

Description of application:

The render is applied by a stainless steel smoother. The structure is consequently formed by smoothing or designing by means of a stainless or plastic smoother. For complete areas material of the same batch should be used. If more batches are to be processed they must be mixed together and uniformly thinned. To observe permanent consistency of the material for adjacent surfaces is essential. Complete areas must done at once with sufficient and trained staff. If it is not possible, the area should be conveniently divided with taking into account possible deviations. Adjacent surfaces (windows, doors, banisters, switchgear boxes etc) must be protected against pollution by a suitable foil, removable or protective paints etc. Any polluted area must be cleaned in time because removal of dried material is difficult.

Flatness requirements:

Maximal grain size + 0,5 mm for 1 m of length.

Climatic conditions during application:

The work may not be done under rain, fog, strong wind nor to directly sunlit surfaces. Range of working temperatures is from +5 °C to +30 °C (air and base) and the applied material must be secured against frost and rain up to complete drying.

Requirements for base maturation:

The render is possible to be applied after complete drying of penetration or base paint depending on the climatic conditions - 4 hours minimally, at temperatures lower than +10 °C and high relative humidity even 24 hours.

Security (R-theorems):

R 52/53 Harmful for aquatic life, it may cause long-term unfavourable effects in water environment.

Safety regulations:

BETADEKOR SAD is not flammable liquid in sense of the ?SN 65 0201 standard, it does not contain toxic organic solvents and it is not classified as dangerous preparation in the sense of Act no. 356/2003 Coll. as amended.

0100 VOC: Product category A , product subcategories I. The maximum permissible limit VOC content in the product ready to use is 200 g/l mass.

Maximum VOC content in the product ready to use is 8,6 g/l mass.

First aid:

Protect your eyes and skin against stain, do not eat, smoke nor drink during the work. After the work wash your hands with water and soap and apply a reparation cream. If your eyes are hit, rinse them with water minimally for 15 minutes. If consumed immediately rinse mouth, drink minimally 0,5 l of water, do not invoke vomiting and always seek medical help.

Recommended tools:

stainless steel smoother, plastic smoother

Quality:

The product as defined ETICS component is in conformity with requirements resulting from the CE marking. The product is certified for the mentioned use and tested by accredited testing laboratory. At production the product is controlled by the company laboratory subject to the certified quality management system subject to the ?SN EN ISO 9001 standard.

Storage:

The product must be stored in original packing protected against humidity, direct sunlight under temperatures minimally +5 °C. Under the mentioned conditions the storage life is 6 months from the production date. Production date is marked on the packing.

Liquidation:

Liquidation of not usable remains is done by avoidance of access of air and after drying it is liquidated as building waste. Used packaging is liquidated as other waste according to the valid legislation.



11

STOMIX, spol. s r. o., 790 65 Žulová 178
Czech Republic, ID: 48400874
EN 15824
External and internal renders
with organic binding agent

Permeability to water vapour: V_2
Permeability of water in liquid phase: W_3
Adhesion: 0,7 MPa
Durability: NPD
Thermal conductivity: 0.8 W(m.k)
Fire resistance: Euroclass F